

M/Y	SVHC candidate	CAS No.	parameter	relevance for shoes and leather goods	comment	limit exceeding (> 0.1 %)
03/10	Acrylamide	79-06-1	amides	plastics, leather, textiles, synthetics	monomer, dyestuff	is not expected
12/12	Diazene-1,2-dicarboxamide (C,C'-azodi-(formamide))	123-77-3		plastics, rubber	foaming agent	possible
10/08	Anthracene	120-12-7	PAH	leather plastics, rubber, elastomers, foams, wood	greasing agent softener, dyestuff, wood preservative	is not expected
01/10	Anthracene oil,	90640-80-5				
01/10	Anthracene oil - Anthracene-low,	90640-82-7				
01/10	Anthracene oil - Anthracene paste,	90640-81-6				
01/10	Anthracene oil - Anthracene fraction,	91995-15-2				
01/10	Anthracene oil - distn. lights	91995-17-4				
06/16	Benzo[a]pyrene	50-32-8				
01/18	Benzo[a]anthracene	56-55-3				
01/18	Chrysene	218-01-9				
06/18	Benzo[ghi]perylene	191-24-2				
01/19	Benzo[k]fluoranthren	207-08-9				
01/19	Fluoranthren	206-44-0 93951-69-0				
01/19	Phenanthren	85-01-8				
01/19	Pyren	129-00-0 1718-52-1				
10/08	4,4'-Diamino-diphenylmethane	101-77-9	aromatic amine	leather, textiles, synthetics, paperboard PUR epoxy resin, adhesives	azo dyestuff basis for isocyanates bonding agent chemical for synthesis	is not expected
12/11	2,2'-Dichlor-4,4'-methylene-dianiline	101-14-4				
12/11	2-Methoxyaniline (o-Anisidine)	90-04-0				
12/12	4,4'-Methylendi-o-toluidine (3,3'-Dimethyl-4,4'-diamino-diphenylmethan)	838-88-0				
12/12	4,4'-Oxidianiline and its salts	101-80-4				
12/12	o-Toluidine (2-Aminotoluene)	95-53-4				
12/12	4-Methyl-m-phenylenediamine (2,4-Toluene-diamine)	95-80-7				

M/Y	SVHC candidate	CAS No.	parameter	relevance for shoes and leather goods	comment	limit exceeding (> 0.1 %)
12/12	6-Methoxy- <i>m</i> -toluidine (<i>p</i> -Cresidine)	120-71-8	aromatic amine	leather, textiles, synthetics, paperboard	azo dyestuff	is not expected
12/12	Biphenyl-4-ylamine	92-67-1				
12/12	<i>o</i> -Aminoazotoluene	97-56-3				
12/12	4-Aminoazobenene (4-Phenylazoaniline)	60-09-3				
12/13	Disodium 3,3'-[[1,1'-biphenyl]-4,4'-diylbis(azo)]bis-(4-aminonaphthalene-1-sulphonate) (C.I. Direct red 28)	573-58-0	aromatic amine (benzidine)	leather, textiles, synthetics, paperboard	azo dyestuff	is not expected
12/13	Disodium 4-amino-3-[[4'-[(2,4-diaminophenyl)-azo]-[1,1'-biphenyl]4-yl]-azo]-5-hydroxy-6-(phenylazo)naphthalene-2,7-disulphonate (C.I. Direct black 38)	1937-37-7				
12/11	Formaldehyde, oligomeric reaction products with aniline	25214-70-4	Formaldehyde	epoxy resin, adhesives	chemical product for processes	is not expected
10/08	Alkanes, C10-13, chloro (short chain chlorinated paraffins)	05535-84-8	chlorinated paraffin's	leather textiles, synthetics, colors, plastics, adhesives	greasing agent flame retardant	possible
12/11	4-(1,1,3,3-Tetramethyl-butyl)-phenol (4-tert.-Octylphenol)	140-66-9	Alkyl phenol	leather textiles, synthetics, plastics, adhesives, rubber	production of phenolic resins, coatings, colors, and varnish; precursor for Ethoxylates (surfactants), Lubricant and grease	possible
12/12	4-Nonylphenol (linear and branched and mixtures of isomers)	-				
01/17	4-heptylphenol, branched and linear	-				
01/18	Reaction products of 1,3,4-thiadiazolidine-2,5-dithione, formaldehyde and 4-heptylphenol, branched and linear (RP-HP) with $\geq 0.1\%$ w/w 4-Heptylphenol, branched and linear (4-HPbl)					
01/17	4-tert-Pentylphenol (<i>p</i> -(1,1-dimethylpropyl)phenol)	80-46-6				

M/Y	SVHC candidate	CAS No.	parameter	relevance for shoes and leather goods	comment	limit exceeding (> 0.1 %)
12/12	4-(1,1,3,3-Tetramethyl-butyl)-phenol ethoxylated (mixture of ethoxylates) (4-tert.-Octylphenol ethoxylates)	-	Alkyl phenol ethoxylate	leather, textiles, synthetics	surfactant, chemical product for processes	possible
06/13	4-Nonylphenol ethoxylated (branched and linear)	-				
06/13	Cadmium	7440-43-9	Heavy metals after total digestion, Cadmium	metall parts plastics (especially PVC)	impurities in metal stabilizing agent	possible
06/13	Cadmium oxide	1306-19-0		plastics	catalyst in sythesis, pigment in glass and ceramic	not expected
06/14	Cadmium chloride	10108-64-2		photovoltaic modules, circuit board production	not expected	
12/13	Cadmium sulphide	1306-23-6		catalyst in sythesis, pigment in plastics, glass and ceramic	possible	
12/14	Cadmium fluoride	7790-79-6		not relevant	laboratory reagent	not expected
12/14	Cadmium sulphate	10124-36-4 31119-53-6				
01/18	Cadmiumnitrate	10325-94-7		plastics	Pigments, Polymeres, Glas	not expected
01/18	Cadmiumhydroxide	21041-95-2		plastics	Pigments, Polymeres, Batteries	not expected
01/18	Cadmiumcarbonate	513-78-0		plastics	Pigments, Polymeres	not expected
10/08	Cobalt dichloride	7646-79-9		Heavy metals after total digestion, Cobalt	rubber, elastomers, soft plastics metal parts	Additive alloys, electroplating humidity indicator in drying agents catalyst, for pigments and dyestuffs, as coloring for glazes
12/10	Cobalt-(II)-carbonate	513-79-1	is not expected			
12/10	Cobalt-(II)-diacetate	71-48-7				
12/10	Cobalt-(II)-dinitrate	10141-05-6				
12/10	Cobalt-(II)-sulfate	10124-43-3				

M/Y	SVHC candidate	CAS No.	parameter	relevance for shoes and leather goods	comment	limit exceeding (> 0.1 %)
12/10	Chromium trioxide	1333-82-0	Heavy metals after total digestion, Chrome	Wood	wood preservative, strong oxidant	is not expected
12/10	Chromic acid and all oligomers	7738-94-5				
12/10	Dichromic acid and all oligomers	13530-68-2				
06/10	Trichloroethylene	79-01-6	VOC	adhesives, leather, textiles	solvent, degreasing agent or cleaning agent	possible
06/11	1,2,3-Trichloropropane	96-18-4		Vinyl chloride		
12/11	1,2-Dichloroethane	107-06-2		leather, textiles, synthetics	solvent for leather and textile coatings, intermediate product of colors and varnish	possible
06/11	1-Methyl-2-pyrrolidone (NMP)	872-50-4		textiles, synthetics	solvent for leather and textile coatings	
12/11	N,N-Dimethylacetamide (DMAC)	127-19-5		coatings, plastics	softener	
12/12	N,N-Dimethylformamide (DMFA)	68-12-2		leather, textiles, synthetics	intermediate product of azo dyestuff; basis for isocyanates, additive in the plastic industry; can appear together with DBP	is not expected
06/12	Formamide	75-12-7		PUR, plastics		
01/10	2,4-Dinitrotoluene	121-14-2		plastics	solvent or degreasing agent	is not expected
12/12	1-Bromopropane	106-94-5		varnishes, leather, textiles, adhesives, dyes, polymers	solvent, leather finish, textile finishing	
12/10	2-Ethoxyethanol	110-80-5		synthetics, adhesives	intermediate product of foaming agents, colors and flame retardants	
12/10	2-Methoxyethanol	109-86-4				
06/11	2-Ethoxyethylacetate	111-15-9	adhesives	solvent in textile production and textile coatings		
06/11	Hydrazine	302-01-2 / 7803-57-8		solvent in the production of industrial chemicals	is not expected	
12/11	Bis-(2-methoxyethyl)-ether (Diethylenglycoldimethylether)	111-96-6			is not expected	
12/12	Furan	110-00-9			is not expected	

M/Y	SVHC candidate	CAS No.	parameter	relevance for shoes and leather goods	comment	limit exceeding (> 0.1 %)
10/08	Dibutyl phthalate (DBP)	84-74-2	phthalate	plastics (especially PVC), synthetics, colors, epoxy resin, adhesives, coatings	softener	possible
12/14	Bis-(2-ethylhexyl)-phthalate (DEHP)	117-81-7				
10/08	Benzyl butyl phthalate (BBP)	85-68-7				
01/10	Diisobutyl phthalate (DIBP)	84-69-5				
06/11	1,2-Benzenedicarboxylic acid, di-C7-11-branched and linear alkyl esters (DHNUP)	68515-42-4				
06/11	1,2-Benzenedicarboxylic acid, di-C6-8-branched alkyl esters, C7-rich (DIHP)	71888-89-6				
12/11	Bis-(2-methoxyethyl)-phthalate (BMEP)	117-82-8				
06/13	Di- <i>n</i> -pentyl phthalate (DPP)	131-18-0				
12/12	Diisopentyl phthalate (DIPP)	605-50-5				
12/12	<i>n</i> -Pentyl-isopentyl phthalate (PIPP)	776297-69-9				
12/12	1,2-Benzenedicarboxylic acid, dipentylester branched and linear	84777-06-0				
12/13	1,2-Benzenedicarboxylic acid, dihexylester branched and linear	84-75-3				
06/14	Dihexyl phthalate (DnHP)	68515-50-4				
06/15	1,2-Benzenedicarboxylic acid, di-C6-10- alkyl esters; 1,2-Benzenedicarboxylic acid, mixed decyl and hexyl and octyl diesters with $\geq 0.3\%$ of diehexyl phthalate	68515-51-5 69648-93-1				
06/18	Dicyclohexylphthalate (DCHP)	84-61-7				
12/12	Hexahydro-2-benzofuran-1,3,dione cis-cyclohexane-1,2-dicarboxylic anhydride trans-cyclohexane-1,2-dicarboxylic anhydride	85-42-7 13149-00-3 14166-21-3	phthalate analogs	plastics	Process additive in Polyester production, softener in plastics	possible
12/12	Hexahydromethylphthalic anhydride Hexahydro-4-methylphthalic anhydride Hexahydro-1-methylphthalic anhydride Hexahydro-3-methylphthalic anhydride	25550-51-0 19438-60-9 48122-14-1 57110-29-9				

M/Y	SVHC candidate	CAS No.	parameter	relevance for shoes and leather goods	comment	limit exceeding (> 0.1 %)
10/08	Hexabromocyclododecane (HBCDD) and all major diastereomers (α -HBCDD, β -HBCDD, γ -HBCDD)	25637-99-4 3194-55-6 134237-50-6 134237-51- 134237-52-8	flame retardant	textiles, synthetics, plastics, leather	electrical appliances furniture; softener for plastics additive in fatliquor	possible
12/12	Bis-(pentabromophenyl)-ether (DecaBDE)	1163-19-5				
01/10	Tris-(2-chloroethyl)-phosphate	115-96-8				
12/13	Trixylyl phosphate	25155-23-1				
01/18	Dodecachloropentacyclo[12.2.1.16,9.02,13.05,10]octadeca-7,15-dien ("Dechlorane Plus" TM , DP oder DPMA)	13560-89-9 135821-74-8 135821-03-3				
10/08	Bis-(tributyltin)-oxid (TBTO)	56-35-9	Tin-organic compounds	textiles, synthetics, plastics, leather	biocide	is not expected
12/12	Dibutyl tin dichloride (DBT)	683-18-1			stabilizing agent, catalyst	possible
12/14	2-ethylhexyl 10-ethyl-4,4-dioctyl-7-oxo-8-oxa-3,5-dithia-4-stannatetradecanoate (DOTE)	15571-58-1				
12/14	reaction mass of 2-ethylhexyl 10-ethyl-4,4-dioctyl-7-oxo-8-oxa-3,5-dithia-4-stannatetradecanoate and 2-ethylhexyl 10-ethyl-4-[[2-[(2-ethylhexyl)oxy]-2-oxoethyl]thio]-4-octyl-7-oxo-8-oxa-3,5-dithia-4-stannatetradecanoate (reaction mass of DOTE and MOTE)	-				
10/08	Sodium dichromate	7789-12-0	Chromium VI	leather, wool textiles, synthetics, plastics metals, coatings	formed from Chromium III by oxidation dyestuff, pigments application in the aeronautics, steel production corrosion prevention	is not expected
06/10	Sodium chromate	7775-11-3				
06/10	Potassium chromate	7789-00-6				
06/10	Potassium dichromate	7778-50-9				
06/10	Ammonium dichromate	7789-09-5				
01/10	Lead chromate	7758-97-6				
06/11	Strontium chromate	7789-06-2				
12/11	Dichromium tris-(chromate)	24613-89-6				
12/11	Potassium hydroxyoctaoxidizincate-dichromate (zinc yellow)	11103-86-9				
12/11	Pentazinc chromate octahydroxide (alkali free zinc yellow)	49663-84-5				

M/Y	SVHC candidate	CAS No.	parameter	relevance for shoes and leather goods	comment	limit exceeding (> 0.1 %)	
10/08	Triethyl arsenate	15606-95-8	Heavy metals after total digestion, arsenic	textiles, wood	biocide, wood preservative	possible	
10/08	Diarsenic pentaoxide	1303-28-2					
10/08	Diarsenic trioxide	1327-53-3					
10/08	Lead hydrogen arsenate	7784-40-9		PVC	stabilizing agent		
12/11	Calcium arsenate	7778-44-1		not relevant	smelting of copper, production of arsenic trioxide smelting of glass, production of printed boards		is not expected
12/11	Trilead arsenate	3687-31-8					
12/11	Arsenic acid	7778-39-4					
06/10	Boric acid	10043-35-3 / 11113-50-1	Heavy metals after total digestion, Boron	rubber, adhesives	biocide, flame retardant	possible	
06/10	Disodium tetraborate, anhydrous	1330-43-4 / 12179-04-3 / 1303-96-4					
06/10	Tetraboron disodium heptaoxide, hydrate	12267-73-1					
06/12	Diboron trioxide	1303-86-2					
06/14	Sodium peroxometaborate	7632-04-4		not relevant	bleaching agent, used in detergents, cosmetic products		is not expected
06/14	Sodium perborate; perboric acid, sodium salt	-					
06/18	Disodiumoctaborate	12008-41-2	not relevant	anti-freeze products, heat transfer fluids, lubricants and greases, and washing and cleaning products	is not expected		

M/Y	SVHC candidate	CAS No.	parameter	relevance for shoes and leather goods	comment	limit exceeding (> 0.1 %)
12/12	lead oxide sulfate	12036-76-9	Heavy metals after total digestion, Lead	plastics	stabilizing agent for plastics e.g. construction industry	possible
12/12	[Phthalato-(2-)]-dioxotrilead	69011-06-9				
12/12	Dioxobis-(stearato)-trilead	12578-12-0				
12/12	Fatty acids, C16-18, lead salts	91031-62-8				
12/12	Lead oxide (Leadmonoxide)	1317-36-8				
12/12	Lead tetroxide (orange lead)	1314-41-6				
12/12	Pentalead tetraoxide sulphate	12065-90-6		plastics (PVC), electronic devises	inter alia electronic and optical parts, batteries, crystal glass	possible
12/12	Sulfurous acid, lead salt, dibasic	62229-08-7				
12/12	Tetralead trioxide sulphate	12202-17-4		leather, textiles, synthetics, plastics	dye stuff, pigments	is not expected
12/12	Trilead dioxide phosphonate	12141-20-7				
01/10	Lead chromate molybdate sulphate red (C.I. Pigment Red 104)	12656-85-8		not relevant	initiating explosives in detonator caps or ammunition	is not expected
01/10	Lead sulfochromate yellow (C.I. Pigment Yellow 34)	1344-37-2				
12/11	Lead azide, Lead diazide	13424-46-9				
12/11	Lead styphnate	15245-44-0				
12/11	Lead dipicrate	6477-64-1				
06/12	Lead-(II)-bis-(methansulfonate)	17570-76-2				
12/12	Acetic acid, lead salt, basic, Lead-(II)-hydroxy acetate (1:1:1)	51404-69-4				
12/12	Trilead bis(carbonate) dihydroxide (basic lead carbonate)	1319-46-6				
12/12	Lead titanium trioxide	12060-00-3				
12/12	Lead titanium zirconium oxide	12626-81-2				
12/12	Lead bis(tetrafluoroborate)	13814-96-5	electronic components (printed board) intermediate product in chemical industry production of semiconductors surface treatment of metals (galvanic and electro plating)	is not expected		
12/12	Lead cyanamidate	20837-86-9				

M/Y	SVHC candidate	CAS No.	parameter	relevance for shoes and leather goods	comment	limit exceeding (> 0.1 %)
12/12	Lead dinitrate	10099-74-8	Heavy metals after total digestion, Lead	not relevant	Process additive in production of dyestuffs and varnishes	is not expected
12/12	Sillic acid, lead salt	11120-22-2			production of crystal glass	
12/12	Tetraethyllead	78-00-2			Additive for fuels	
12/12	Pyrochlore, antimony lead yellow	8012-00-8			pigment for paint, varnish	
12/12	Sillic acid, barium salt, lead-doped	68784-75-8			coating for glass	
12/13	Lead di(acetate)	301-04-2			paint stripper	
06/18	Lead	7439-92-1		Metal Parts, catalyst in plastic production used as salt or in organic compounds	Metals, Plastics	possible
12/14	2-benzotriazol-2-yl-4,6-di-tert-butylphenol (UV-320)	3846-71-7	UV Stabilizers	plastics, coatings	UV stabilizer in multiple plastics and coatings	possible
12/14	2-(2H-benzotriazol-2-yl)-4,6-ditertpentylphenol (UV-328)	25973-55-1				
12/15	2,4-di-tert-butyl-6-(5-chlorobenzotriazol-2-yl)-phenol (UV-327)	3864-99-1				
12/15	2-(2H-benzotriazol-2-yl)-4-(tert-butyl)-6-(sec-butyl)-phenol (UV-350)	36437-37-3				
01/19	3-BC or 3-Benzylidencampher or 1,7,7-Trimethyl-3-(phenylmethylen) bicyclo[2.2.1]heptan-2-on)	15087-24-8	UV Filter	Not relevant	Cosmetics	is not expected

M/Y	SVHC candidate	CAS No.	parameter	relevance for shoes and leather goods	comment	limit exceeding (> 0.1 %)
06/12	4,4'-bis(dimethylamino)-4''-(methylamino)-trityl alcohol [with ≥ 0.1% of Michler's ketone]	561-41-1	Michler's reagent	textiles, synthetics, plastics	Michler's ketone: additive compound and intermediate of dyes and pigments writing inks and other inks, purifiers, coatings paper dying	is not expected
06/12	[4-[4,4'-bis(dimethylamino)-benzhydrylidene]-cyclohexa-2,5-dien-1-ylidene]-dimethylammonium chloride (C.I. Basic Violet 3) [with ≥ 0.1% of Michler's ketone]	548-62-9				
06/12	4,4'-bis(dimethylamino)-benzophenone (Michler's ketone)	90-94-8				
06/12	[4-[[4-anilino-1-naphthyl]-[4-(dimethylamino)phenyl]-methylene]-cyclo-hexa-2,5-dien-1-ylidene]-dimethylammonium chloride (C.I. Basic Blue 26) [with ≥ 0.1% of Michler's ketone]	2580-56-5				
06/12	α,α-Bis[4-(dimethylamino)phenyl]-4-(phenylamino)-naphthalene-1-methanol (C.I. Solvent Blue 4) [with ≥ 0.1% of Michler's ketone]	6786-83-0				
06/12	N,N,N',N'-tetramethyl-4,4'-methylenedianiline (Michler's base)	101-61-1				
12/12	Propylene oxide (1,2-epoxypropane, Methyloxirane)	75-56-9	Epoxide	Leather, textiles, synthetics, plastics	Monomer for production of polymers, surfactants and dyeing auxiliary	is not expected
12/13	Imidazolidine-2-thione; 2-Imidazolone-2-thiol	96-45-7	-	Neoprene, polyacryl-rubber	Additive for vulcanization	possible
06/12	1,3,5-Tris(oxiran-2-ylmethyl)-1,3,5-triazinane-2,4,6-trione (TGIC)	2451-62-9	Isocyanuric acid derivatives	coatings, adhesives, plastics	hardener in resins and coatings	is not expected
06/12	1,3,5-Tris[(2S,2R)-2,3-epoxypropyl]-1,3,5-triazine-2,4,6-(1H,3H,5H)-trione (β-TGIC)	59653-74-6				

M/Y	SVHC candidate	CAS No.	parameter	relevance for shoes and leather goods	comment	limit exceeding (> 0.1 %)
12/12	Pentacosafuorotridecanoic acid	72629-94-8	Perfluorinated carboxylic acids	textiles, leather	water-repellent finishes for shoes and apparel	possible
12/12	Tricosafuorododecanoic acid	307-55-1				
12/12	Henicosafuoroundecanoic acid	2058-94-8				
12/12	Heptacosafuorotetradecanoic acid	376-06-7				
06/13	Pentadecafluorooctanoic acid (PFOA)	335-67-1				
06/13	Ammonium pentadecafluorooctanoate (APFO)	3825-26-1				
12/15	Perfluorononan-1-oic-acid and its sodium and ammonium salt	375-95-1 21049-39-8 4149-60-4				
01/17	Nonadecafluorodecanoic acid (PFDA) and its sodium and ammonium salts	335-76-2 3830-45-3 3108-42-7				
07/17	Perfluorhexane-1-sulphonic acid and its salts (PFHxS)	-				
01/17	Bisphenol A (BPA) (4,4'-isopropylidenediphenol)	80-05-7	Bisphenol A	Adhesives, Polycarbonat	Epoxid resins and in polycarbonat	possible
01/19	BisP-MIBK (2,2-Bis (4'-hydroxyphenyl) -4-methylpentane)	6807-17-6	Bisphenol			
12/11	Phenolphthalein	77-09-8	-	not relevant	laboratory reagent	is not expected
06/12	1,2-Dimethoxyethane, ethylene glycol dimethyl ether (EGDME)	110-71-4	-		is not expected	
06/12	1,2-Bis(2-methoxy-ethoxy)-ethane; (TEGDME, triglyme)	112-49-2	-		solvent for chemical synthesis	is not expected
12/12	1,2-Diethoxyethane (EGDEE, diethyl glycol)	629-14-1	-		is not expected	
10/08	5-tert-butyl-2,4,6-trinitro-m-xylene (musk xylene)	81-15-2	-		cosmetics	is not expected

M/Y	SVHC candidate	CAS No.	parameter	relevance for shoes and leather goods	comment	limit exceeding (> 0.1 %)
01/10	Pitch, coal tar, high temperature	65996-93-2	-	Not relevant	steel industry, coal and coke fabrication	is not expected
12/15	1,3-Propansultone	1120-71-4			intermediate in synthesis of chemicals	
12/11	Zirconia Aluminosilicate Refractory Ceramic Fibres (Zr-RCF)	-			electrical and home appliances, high temperature isolation in industrial facilities, fire prevention	
12/11	Aluminosilicate Refractory Ceramic Fibres (RCF)	-			industrial intermediate, laboratory reagent	
12/12	Diethyl sulfate	64-67-5			intermediate in synthesis of chemicals	
12/12	Dimethyl sulfate	77-78-1			Process additive	
12/12	Dinoseb (2-(1-Methylpropyl)-4,6-dinitrophenol; DNBP)	88-85-7			biocide in lubricants, hardening agent for PUR	
12/12	Methoxy acetic acid	625-45-6				
12/12	N-Methylacetamid	79-16-3				
12/12	3-Ethyl-2-methyl-2-(3-methylbutyl)-1,3-oxazolidine	143860-04-2				
06/15	5-Sec-Butyl-2-(2,6-dimethylcyclohex-3-en-1-yl)-5-methyl-1,3-dioxan [1], 5-Sec-Butyl-2-(2,4-dimethylcyclohex-3-en-1-yl)-5-methyl-1,3-dioxan [2] [covering any of the individual isomers of [1] or [2] or any combination thereof]	117933-89-8 343934-04-3 343934-05-4 676367-02-5 676367-03-6 676367-04-7 676367-05-8 676367-06-9 676367-07-0 676367-08-1 676367-09-2 186309-28-4	-	not relevant	Process additive Intermediate in synthesis of chemicals	is not expected
12/15	Nitrobenzene	98-95-3	-			

M/Y	SVHC candidate	CAS No.	parameter	relevance for shoes and leather goods	comment	limit exceeding (> 0.1 %)
06/18	Octamethylcyclotetrasiloxane (D4)	556-67-2	Silicons	Silicone, Silicone or Siloxane coated materials	Silicone	possible
06/18	Decamethylcyclopentasiloxane (D5)	541-02-6				
06/18	Dodecamethylcyclohexasiloxane (D6)	540-97-6				
06/18	Terphenyl, hydrogenated	61788-32-7	-	Prints	plastic additive, solvent, in coatings/inks, in adhesives and sealants, and heat transfer fluids	is not expected
06/18	Ethylenediamine (EDA)	107-15-3	-	Not relevant	adhesives and sealants, coating products, fillers, putties, plasters, modelling clay, pH regulators	is not expected
06/18	Benzene-1,2,4-tricarboxylic acid 1,2 anhydride (TMA) Trimellitacidanhydride	CAS 552-30-7	Organic Acids	Not relevant	manufacture of esters and polymers	is not expected